



LOCTITE[®] 205[™]

February 2007

PRODUCT DESCRIPTION

LOCTITE[®] 205[™] provides the following product characteristics:

Technology	Acrylic
Chemical Type	Methacrylate ester
Appearance (uncured)	Creamy light orange dispersion ^{LMS}
Viscosity	High
Components	
Cure	Anaerobic
Application	Threadlocking, Sealing

LOCTITE[®] 205[™] is a dry-to-the-touch, preapplied film for threaded fasteners. It remains inert on the fastener until assembly of the threads releases a quick curing resin. The resin fills all the voids in the threads and cures to securely lock and seal the assembly. LOCTITE[®] 205[™] prevents loosening through vibration to provide locking and sealing of threaded assemblies. Typical applications include locking carburetor screws, transmission nuts, head bolts, truck axle bolts and tower bolts and also for sealing transmission bolts and pipe plugs and fittings. This product is typically used in applications with an operating range of -54 °C to +150 °C.

NOTE: LOCTITE[®] 205[™] is not recommended for use on copper or brass surfaces.

TYPICAL PROPERTIES OF UNCURED MATERIAL


Flash Point - See MSDS
 Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):
 Spindle 5, speed 2 rpm 80,000 to 150,000^{LMS}

TYPICAL CURING PERFORMANCE

On Part Life, years 4


Cure Speed vs. Substrate

The graph below shows the breakaway strength developed with time on 3/8 x 16 phosphate and oil nuts & bolts compared to different materials and tested according to ISO 10964.



Cure Speed vs. Temperature

The graph below shows the breakaway strength developed with time at different temperatures on 3/8 x 16 phosphate and oil nuts & bolts.



TYPICAL PERFORMANCE OF CURED MATERIAL

Adhesive Properties

After 72 hours @ 22 °C

Breakaway Torque, ISO 10964: 3/8 x 16 phosphate and oil nuts and bolts	N·m 17 (lb.in.) (149)
Prevail Torque, ISO 10964: 3/8 x 16 phosphate and oil nuts and bolts	N·m 6 (lb.in.) (57)

On - Torque, : M10 nuts (plain finish) and phosphate and oil bolts	N·m <2.0 ^{LMS} (lb.in.) (17.7)
---	--


Breakaway Torque, : M10 nuts (plain finish) and phosphate and oil bolts	N·m ≥22 ^{LMS} (lb.in.) (194)
--	--

Prevail Torque, : M10 nuts (plain finish) and phosphate and oil bolts	N·m ≥5.6 ^{LMS} (lb.in.) (49)
--	--

TYPICAL ENVIRONMENTAL RESISTANCE


Cured for 72 hours @ 22 °C
 Breakaway Torque, ISO 10964:
 3/8 x 16 phosphate and oil nuts and bolts

Hot Strength
 Tested at temperature



Heat Aging

Heat aged for 2000 hours, tested at temperature



Chemical/Solvent Resistance

Aged under conditions indicated and tested @ 22 °C

Environment	°C	% of initial strength		
		100 h	500 h	1000 h
Motor oil	125	132	109	94
Motor oil	87	158	152	142
Unleaded gasoline	22	113	82	77
Brake fluid	22	116	101	93
Ethanol	22	116	75	73
1,1,1 Trichloroethane	22	108	90	84
Water/glycol 50/50	87	158	134	127
ATF	125	125	102	93
Methanol/Unleaded 15/85	25	112	79	74

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure and performance of the adhesive.

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). Users are recommended to confirm compatibility of the product with such substrates.

Directions for use

LOCTITE® 205™ is applied to threaded parts by authorized process centers who have automatic fastener cleaning, feeding, coating, rust proofing and drying equipment. Quantities can be handled promptly with minimum turnaround time. Sample fittings should be sent to the nearest authorized process center where they will coat your parts and return them to you for evaluation. SAMPLE TESTS ARE RECOMMENDED TO OBTAIN DESIRED RESULTS ON YOUR PARTS. Contact the nearest Loctite Sales Representative for the authorized process center nearest to you.

Loctite Material Specification^{LMS}

LMS dated April 10, 1996. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties. Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0